



ARLON

## ▶ SLX™ Cast Wrap Film

### Premium Cast Digital Film with FLITE Technology™

SLX™ Cast Wrap is a 2-mil (50 micron) premium gloss white repositionable cast film with FLITE Technology™. Designed for full and partial vehicle and fleet applications, the film allows for a fast install, conforming around rivets, complex curves and deep channels with ease. FLITE Technology is a lite contact system allowing graphics to float over a substrate until firm pressure is applied. It guarantees the fastest installation while ensuring long-term bond and clean removability. SLX Cast Wrap has a tinted, permanent pressure-sensitive adhesive providing excellent opacity. The low profile, air egress liner aids with easy installation, resulting in a smooth finish. Arlon strongly recommends the use of Series 3270 Overlamine when using SLX Cast Wrap for optimum performance of the film. SLX Cast Wrap is rated for outdoor durability up to 7 years (unprinted). Printed durability is dependent on the ink system used.

### APPLICATIONS & FEATURES

- Ideal for full or partial vehicle and fleet wraps.
- Fast, easy application for the novice and experienced installers.
- Vibrant and reliable print quality on Eco-Solvent, Solvent, UV and Latex print systems.
- Easy liner release maintaining the integrity of the graphic.

Certified for  
HP Latex Inks

### PERFORMANCE & PHYSICAL DATA

PROPERTY	TEST METHODS	TYPICAL VALUE	
<b>SURFACE FINISH</b>	Gloss Meter 60° Reflection	70 to 90 Gloss Units	
<b>THICKNESS</b>	Micrometer, Federal Bench Type	2-mil (50 micron)	
<b>TENSILE STRENGTH</b>	Tensile Tester with 2-in (51 mm) jaw separation; crosshead speed of 12 in/min. (5.1 mm/s), web direction	≥ 4.5 lb/in	≥ 0.8 kg/cm
<b>ELONGATION</b>	Instron Tensile Tester as above	Average 190%	
<b>SHELF LIFE (IN BOX)</b>	Ideal Storage Temperature 70°F (21°C) and 50% relative humidity	2 years from factory shipment	
<b>APPLICATION TEMPERATURE RANGE</b>	On clean, dry substrate	40°F to 100°F	4.4°C to 38°C
	On clean, dry substrate (corrugated with rivets and channels)	60°F to 100°F	15°C to 38°C
<b>SERVICE TEMPERATURE RANGE</b>	On clean, dry substrate	-40°F to 176°F	-40°C to 80°C
<b>DIMENSIONAL STABILITY</b>	158°F (70°C), 48 hours	0.010 in	0.24 mm
<b>PEEL ADHESION</b>	PSTC-1, 15 min, 70°F (21°C)	≥ 2.4 lb/in	≥ 420 N/m
	PSTC-1, 24 hours, 70°F (21°C)	≥ 3.0 lb/in	≥ 525 N/m
	PSTC-1, 1 week, 70°F (21°C)	≥ 4.2 lb/in	≥ 736 N/m
<b>LINER RELEASE</b>	TLMI Release at 90°, 300 in/min (760 cm/min)	50 g/2 in	9.84 g/cm

NOTE: Recommended post-heat surface temperature of vinyl installed: 203°F to 221°F (95°C to 105°C). The recommended post-heat temperature applies to the film and overlamine wrap. Standard Terms & Conditions Apply.

## OPTIMUM PERFORMANCE

Actual weathering durability depends on surface preparation, surface maintenance and exposure conditions. Successful weather resistance is characterized by the retention of legibility. SLX Cast Wrap will resist weathering best when applied to vertical or upper outboard angles. Horizontal surfaces, such as hood(s) and auto roof(s), will deteriorate more quickly than vertical surfaces. This is due to increased exposure to sun and moisture, as well as high deposition of dirt and atmospheric contaminants. Use heat and/or chemicals when removing graphics from vehicle (see Installer Handbook for details).

## STORAGE AND MAINTENANCE


Storing vinyl graphics in covered areas will help prolong the life of the vinyl by limiting its exposure to damaging elements such as sunlight and rain. Protecting a wrapped car in the garage can keep it sheltered from all types of weather and harmful pollution, both of which could wear out the horizontal surfaces of the car and cause damage to the paint underneath. Vinyl that starts to brown or show discoloration has been negatively affected by acidic pollutants and if not immediately removed could stain the paint. Taking extra steps to keep the vinyl covered when not in use will help extend the life of the vinyl and keep the car looking as good as it did when it was first wrapped.

## TERMS & CONDITIONS


*The following is made in lieu of all warranties expressed or implied:*


All statements, technical information and recommendations published by Arlon relating to Arlon products are based on tests believed to be reliable and within the accuracy of the equipment used to obtain the specific values. Their accuracy or completeness is not guaranteed and Arlon makes no warranty with regard thereto. Seller's and manufacturer's only responsibility shall be to replace any quantity of the product proved defective. Seller and manufacturer shall not be liable for injury, loss or damage, direct or consequential, arising out of use or the inability to use the product. Nor shall seller or manufacturer be liable for any costs or expenses incurred in the processing or printing on the product. Before using, user shall determine the suitability of the product for its intended use. User assumes all risk and liability of every nature in connection therewith. No statements or recommendations other than those contained in the technical information published by Arlon shall have force or effect unless contained in an agreement manually signed by the officers of seller and manufacturer.


June 2017

USA:  200 Boysenberry Lane, Placentia, CA 92870, USA

EUROPE:  North Sea Building, Gevers Deynootweg 93, 4th Floor, 2586BK Den Haag, The Netherlands

 800 232 7161/+1 714 985 6300

 +31 70 354 4311

 800 329 2756

 +31 70 355 7721

arlon.com