

## Product description

Semi matt vinyl material for heat transfer applications.

**Thickness:** 105 microns (USA: 4.1 mils) for black and white and 125 microns (USA: 4.9mils) for other colors.

**Carrier:** Self-adhesive and clear polyester.

**Norm:** Oeko-Tex label standard 100 Class II. (Except for ref. 134 – 184 – 115 – 186 – 118 – 189)

## Suitable for

Cotton, polyester, acrylic and similar fibres.

## Application advice

- 1) Cut the material in reverse with regular flex blade.
- 2) Weed the excess material.
- 3) Heat press the transfer on the garment with its polyester carrier protected by a silicone paper at 150°C (USA: 300°F) – 10-15 seconds – medium pressure.
- 4) Peel the carrier off when cold.

## Maintenance

Always respect the instructions mentioned on garments.  
After heat pressing, wait 24 hours before the first wash.

**Washing:** 90°C (USA: 190°F) max. inside out - without bleach or any aggressive washing products.

**Tumble-drying:** yes

**Dry cleaning:** no

**Ironing:** backside

**Storage of the roll:** vertically, one year in a dry room, 15-30°C (USA: 60-85°F), protected from sunlight.

## Caution

Those recommendations are based on our own experience.  
We always recommend making trials before starting standard production.

January 2013



8 rue Auguste Poncetton BP 30164  
42004 St Etienne cedex 1 (FRANCE)  
Tel. +33 (0)4 77 49 20 90  
Fax +33 (0)4 77 25 79 82  
info@chemica.fr  
[www.chemica.fr](http://www.chemica.fr)



5300 Oakbrook Parkway  
Building 300 – Suite 368  
Norcross, GA 30093  
Tel. 404-495-5991  
rosa.lopes@chemica.fr  
[www.chemica.fr](http://www.chemica.fr)



RM 2207-9 Tower two lippo ctr  
89 Queensway Admiralty  
HONG KONG  
Cell. +86 1 809 894 8623  
Cell.2 +33 6 34 51 25 58  
Tel. +86 755 8655 0610  
info@chemica.fr  
[www.chemica.fr](http://www.chemica.fr)