

### Product description

Matt and elastic polyurethane material for heat transfer.

**Thickness** : 50-60 microns.

**Carrier** : Transparent adhesive polyester.

### Suitable for

Elastic textiles.

### Application advises

- 1) Cut the material in negative with a regular flex blade.
- 2) Weed the excess material.
- 3) Put the material on the textile and heat press it at 160°C (USA : 300-320°F) with the polyester carrier and protect it with a silicon paper – 20 seconds – with a medium pressure.
- 4) Remove the polyester (cold).

### Maintenance

Always respect the instructions mentioned on garments.  
After heat pressing, wait 24 hours before the first wash.

**Washing** : 60°C (USA : 140°F) max. Inside out - without bleach or any aggressive washing products.

**Tumble-drying**: no

**Dry cleaning**: no

**Ironing**: backside

**Storage of the roll**: vertically, one year in a dry room, 15-25°C (USA : 60-80°F), protected from sunlight.

### Caution

Those recommendations are based on our own experiences.  
We always recommend making trials before starting standard production.

October 2012



8 rue Auguste Poncetton BP 30164  
42004 St Etienne cedex 1 (FRANCE)  
Tel. +33 (0)4 77 49 20 90  
Fax +33 (0)4 77 25 79 82  
info@chemica.fr  
www.chemica.fr



3495 Piedmont road Bldg.11, suite 710  
ATLANTA, GA 30305 (USA)  
Tel. +1 4074 495 5991  
Fax +1 404 233 8625  
rosa.lopes@chemica.fr  
www.chemica.fr



RM 2207-9 Tower two lippo ctr  
89 Queensway Admiralty HONG KONG  
Cell. +33 (0)6 34 51 25 58  
Tel. +33 (0)4 77 49 20 97  
info@chemica.fr  
www.chemica.fr